


LAMINATI A CALDO A U



PROFILO					Momento resistenza Wx	Peso Kg/ml.
U	h	b	a	e		
Speciale						
25	25	12	4	4		1,30
30	30	15	5	5		1,98
35	35	17	4	5		2,15
40	40	20	5	6		3,25
50	50	25	6	6		4,15
60	60	30	6,5	6,5		5,45
Normale						
30	30	33	5,0	7,0	4,3	4,27
40	40	35	5,0	7,0	7,1	4,87
50	50	38	5,0	7,0	10,6	5,59
65	65	42	5,5	7,5	17,7	7,09
80	80	45	6,0	8,0	26,5	8,64
100	100	50	6,0	8,5	41,1	10,60
120	120	55	7,0	9,0	60,7	13,35
140	140	60	7,0	10,0	86,4	16,01
160	160	65	7,5	10,5	116,0	18,84
180	180	70	8,0	11,0	150,0	21,98
200	200	75	8,5	11,5	191,0	25,28
220	220	80	9,0	12,5	245,0	29,36
240	240	85	9,5	13,0	300,0	33,21
260	260	90	10,0	14,0	371,0	37,92
280	280	95	10,0	15,0	448,0	41,84
300	300	100	10,0	16,0	535,0	46,16
320	320	100	14,0	17,5	679,0	59,50
350	350	100	14,0	16,0	734,0	60,60
380	380	102	13,5	16,0	829,0	63,10
400	400	110	14,0	18,0	1020,0	71,80